



CLT- WAND Elemente

Stärke	Aussenlage	Aufbau	Lamellenstärke in mm							
			Q	L	Q	L	Q	L	Q	L
60 mm	quer	3	20	20	20					
70 mm	quer	3	20	30	20					
80 mm	quer	3	30	20	30					
90 mm	quer	3	30	30	30					
100 mm	quer	3	30	40	30					
110 mm	quer	3	40	30	40					
120 mm	quer	3	40	40	40					
100 mm	quer	5	20	20	20	20	20			
110 mm	quer	5	20	20	30	20	20			
120 mm	quer	5	30	20	20	20	30			
130 mm	quer	5	30	20	30	20	30			
140 mm	quer	5	30	20	40	20	30			
150 mm	quer	5	30	30	30	30	30			
160 mm	quer	5	40	20	40	20	40			

CLT- DECKEN&DACH Elemente

Stärke	Aussenlage	Aufbau	Lamellenstärke in mm							
			Q	L	Q	L	Q	L	Q	L
60 mm	längs	3	20	20	20					
70 mm	längs	3	20	30	20					
80 mm	längs	3	30	20	30					
90 mm	längs	3	30	30	30					
100 mm	längs	3	40	20	40					
110 mm	längs	3	40	30	40					
120 mm	längs	3	40	40	40					
100 mm	längs	5	20	20	20	20	20			
110 mm	längs	5	20	20	30	20	20			
120 mm	längs	5	30	20	20	20	30			
130 mm	längs	5	30	20	30	20	30			
140 mm	längs	5	40	20	20	20	40			
150 mm	längs	5	40	20	30	20	40			
160 mm	längs	5	40	20	40	20	40			
170 mm	längs	5	40	30	30	30	40			
180 mm	längs	5	40	30	40	30	40			
190 mm	längs	5	40	40	30	40	40			
200 mm	längs	5	40	40	40	40	40			
180 mm	längs	7	20	40	20	20	20	40	20	
200 mm	längs	7	20	40	20	40	20	40	20	
220 mm	längs	7	30	40	30	20	30	40	30	
240 mm	längs	7	30	40	30	40	30	40	30	



Decklage der Plattenrichtung -> **längs**

Decklage der Plattenrichtung -> **quer**